



Test
TS EN ISO/IEC 17025
AB-0716-T

AB-0716-T

TURT200168099
_REVISED01

12-20

TEST REPORT

Page 1 of 11

REPORT NUMBER : TURT200168099_REVISED01
APPLICANT NAME ZENO ENDÜSTRİ SANAYİ ÜRÜNLERİ ANONİM ŞİRKETİ
ADDRESS Üniversite Mah. Civan Sk. Allure Tower İstanbul No:1 İç Kapı No: 327
Avcılar/İstanbul
Attention : Nergiz Üstal (nergiz@mutlupatent.com)
SAMPLE DESCRIPTION : One sample of "Ice Cubes" Board Game
DATE IN: 16 December, 2020 (16:35)
DATE OUT : 22 December, 2020 / 31 December, 2020
TESTED MODEL NO : 2004
CLAIMED MODEL NO : -
COUNTRY OF ORIGIN : NOT GIVEN
AGE GRADING : 3+
NOTE: In this revised 01 report, Applicant name and address were changed by the request of the applicant.
This report replaced the report no TURT200168099 dated on 22 December, 2020 and must be used instead of it.
Report no TURT200168099 dated on 22 December, 2020 is invalid.

Ezgi Aleyna Arı
Customer Care Executive

Zeynep Akın
Chemical Laboratory
Manager

Nida Arslanbay
Textile Laboratory Manager

Recep Yarlığan
Toys&Hardline/Footwear
Laboratory Manager

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com



200168099_REV01

RESULTS

Page 2 of 11

REPORT :TURT200168099_REVISIED01

31 December, 2020

Test Method	Result	Requirements
TEST	Sample	
SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES	P	
SAFETY OF TOYS – PART 2: FLAMMABILITY	P	
SAFETY OF TOYS – PART 3: MIGRATION OF CERTAIN ELEMENTS	P	
PHthalate Content	P	
POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS	P	
DETECTION OF AMINES DERIVED FROM AZOCOLLOURANTS AND AZODYES	NA	
BENZENE DETERMINATION	NA	

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

RESULTS

Page 3 of 11

REPORT :TURT200168099_REVISED01

31 December, 2020

Test Method	Result	Requirements
PARTS		
1	Blue plastic body	
2	White plastic part	
3	Light blue plastic part	
4	Black plastic part	
5	White textile pocket	
6	White thread	
7	Multicolor carton box	
8	White inner paper	

Remark: Only suitable parts tested for the related tests.

RESULTS

Page 4 of 11

REPORT :TURT200168099_REVISED01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES

BS EN 71 – 1: 2014 + A1 : 2018

The item was labelled: "Warning. Choking Hazard: Small parts. Not for children under 3 years."

The item was tested for children aged over 36 months.

The item was packaging in a cardboard box covered by shrink film which was considered to be disposable.

SECTION	TEST	RESULTS
4	General Requirements	
4.1	Material	Pass
4.7	Edges	Pass
4.8	Point & Metallic Wires	Pass
7	Warning and Instruction for Use	##
7.2	Toys not intended for children under 36 months	Pass

R E S U L T S

Page 5 of 11

REPORT :TURT200168099_REVISED01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

The text of this note is for information only and the indents do not constitute requirements of this European Standard. The information is not exhaustive and Directive 2009/48/EC and the associated guidance documents should be consulted for further details.

The toy or, its packaging or document accompanying must be labelled with:

- The name and address of the manufacturer** **(Not Present)**
- The name and address of the importer.** **(Not Present)**
- Type, batch, serial or model number or other element allowing of toy identification **(Not Present)**
- A CE mark in the correct shape and size. **(Present)**
- Warning and other information should be in the national language(s) of the countries where the toy is marketed.

** In the case of the toy sell in European countries, the toy, its packaging or document accompanying must be labelled with the name and address of the manufacturer and importer.

RESULTS

Page 6 of 11

REPORT :TURT200168099_REVISED01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

SAFETY OF TOYS – PART 2: FLAMMABILITY

BS EN 71-2 : 2020

SECTION	TEST	RESULTS
4.1	General	
	Celluloid (cellulose nitrate) and materials with same burning behaviour in fire	Pass

The test results thus obtained can not be considered as providing an overall indication of the potential fire hazard of toys or materials when subjected to other sources of ignition.

RESULTS

Page 7 of 11

REPORT :TURT200168099_REVISED01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

SAFETY OF TOYS – PART 3: MIGRATION OF CERTAIN ELEMENTS

BS EN 71-3:2019

Acid extraction method was used and migration elements content were determined by Inductively Coupled Plasma-ICP_MS.

	Results (mg/kg)				Detection Limit (mg/kg)	Requirements (mg/kg) Category III
	Part 1	Part 2	Part 3	Part 4		
Antimony (Sb)	ND	ND	ND	ND	0,125	560
Arsenic (As)	ND	ND	ND	ND	0,125	47
Barium (Ba)	ND	ND	ND	ND	0,125	18750
Cadmium (Cd)	ND	ND	ND	ND	0,125	17
Chromium (III)	ND	ND	ND	ND	0,125	460
Chromium (VI)	ND	ND	ND	ND	0,005	0,053
Lead (Pb)	ND	ND	ND	ND	0,125	23
Mercury (Hg)	ND	ND	ND	ND	0,0125	94
Selenium (Se)	ND	ND	ND	ND	0,125	460
Aluminium (Al)	ND	ND	ND	ND	0,125	70000
Boron (B)	ND	ND	ND	ND	0,125	15000
Cobalt (Co)	ND	ND	ND	ND	0,125	130
Copper (Cu)	ND	ND	ND	ND	0,125	7700
Manganese (Mn)	ND	ND	ND	ND	0,125	15000
Nickel (Ni)	ND	ND	ND	ND	0,125	930
Strontium (Sr)	ND	ND	ND	ND	0,125	56000
Tin (Sn)	ND	ND	ND	ND	0,125	180000
Organic tin Δ	ND	ND	ND	ND	0,125	12
Zinc (Zn)	ND	ND	ND	ND	0,125	46000

Δ = Confirmation test was performed on the tested component. The reported value was the sum of the migration values of Methyl tin, Butyl tin, Dibutyl tin, Tributyl tin, Tetrabutyl tin, n- Octyl tin, Di-n-octyl tin, Di-n-propyl tin, Diphenyl tin and Triphenyl tin after converted to Tributyl tin by calculation.

ppm (Part per million)
ND

=mg / kg
=Not Detected

RESULTS

Page 8 of 11

REPORT :TURT200168099_REVISD01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

SAFETY OF TOYS – PART 3: MIGRATION OF CERTAIN ELEMENTS

BS EN 71-3:2019

Acid extraction method was used and migration elements content were determined by Inductively Coupled Plasma-ICP_MS.

	Results (mg/kg)				Detection Limit (mg/kg)	Requirements (mg/kg) Category III
	Part 5	Part 6	Part 7	Part 8		
Antimony (Sb)	ND	ND	ND	ND	0,125	560
Arsenic (As)	ND	ND	ND	ND	0,125	47
Barium (Ba)	ND	ND	2.6	10.4	0,125	18750
Cadmium (Cd)	ND	ND	ND	ND	0,125	17
Chromium (III)	ND	ND	ND	ND	0,125	460
Chromium (VI)	ND	ND	ND	ND	0,005	0,053
Lead (Pb)	ND	ND	ND	1.4	0,125	23
Mercury (Hg)	ND	ND	ND	ND	0,0125	94
Selenium (Se)	ND	ND	ND	ND	0,125	460
Aluminium (Al)	ND	ND	25.5	462.9	0,125	70000
Boron (B)	ND	ND	8.0	30.9	0,125	15000
Cobalt (Co)	ND	ND	ND	ND	0,125	130
Copper (Cu)	ND	ND	ND	2.5	0,125	7700
Manganese (Mn)	ND	ND	9.9	12.0	0,125	15000
Nickel (Ni)	ND	ND	ND	ND	0,125	930
Strontium (Sr)	ND	ND	45.7	39.2	0,125	56000
Tin (Sn)	ND	ND	ND	ND	0,125	180000
Organic tin Δ	ND	ND	ND	ND	0,125	12
Zinc (Zn)	ND	ND	ND	17.2	0,125	46000

Δ = Confirmation test was performed on the tested component. The reported value was the sum of the migration values of Methyl tin, Butyl tin, Dibutyl tin, Tributyl tin, Tetrabutyl tin, n- Octyl tin, Di-n-octyl tin, Di-n-propyl tin, Diphenyl tin and Triphenyl tin after converted to Tributyl tin by calculation.

ppm (Part per million)
ND

=mg / kg
=Not Detected

RESULTS

Page 9 of 11

REPORT :TURT200168099_REVISED01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis

	Part 1&2&3	Part 4
DIBUTYL PHTHALATE (DBP)	ND	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND	ND
BENZYL BUTYL PHTHALATE (BBP)	ND	ND
SUM OF THREE PHTHALATES	ND	ND
DI-ISO-NONYL PHTHALATE (DINP)	ND	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND	ND
SUM OF THREE PHTHALATES	ND	ND

ND

=Not Detected

ppm (part per million)

=mg / kg

Detection Limit

=DIDP, DINP: 100 ppm, Other Phthalates: 10 ppm

LIMIT (MAX.)

=DBP,DEHP,BBP < 1000 ppm ; DINP, DNOP, DIDP < 1000 ppm

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

RESULTS

Page 10 of 11

REPORT :TURT200168099_REVISIED01

31 December, 2020

Test Method	Result	Requirements
-------------	--------	--------------

POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS

AfPS GS 2019:01

	Part 1&2&3	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	0.5 ppm
2	Benzo (e) pyrene	Not Detected	0.5 ppm
3	Benzo (a) anthracene	Not Detected	0.5 ppm
4	Benzo (b) fluoranthene	Not Detected	0.5 ppm
5	Benzo (j) fluoranthene	Not Detected	0.5 ppm
6	Benzo (k) fluoranthene	Not Detected	0.5 ppm
7	Chrysene	Not Detected	0.5 ppm
8	Dibenzo (a,h) anthracene	Not Detected	0.5 ppm

	Part 4	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	0.1 ppm	0.5 ppm
2	Benzo (e) pyrene	0.1 ppm	0.5 ppm
3	Benzo (a) anthracene	Not Detected	0.5 ppm
4	Benzo (b) fluoranthene	Not Detected	0.5 ppm
5	Benzo (j) fluoranthene	Not Detected	0.5 ppm
6	Benzo (k) fluoranthene	Not Detected	0.5 ppm
7	Chrysene	Not Detected	0.5 ppm
8	Dibenzo (a,h) anthracene	Not Detected	0.5 ppm

ppm (part per million) = mg / kg
Detection Limit = 0.1 ppm

RESULTS

REPORT :TURT200168099_REVIS01

Page 11 of 11

31 December, 2020

Test Method

Result

Requirements

SAMPLE PHOTO



TESTED PHOTO



END OF TEST REPORT